



## **EPDM Style AB-563**

**Manufacturer – American Biltrite**

Gaskets meet the pressure ratings, drilling and dimensions of ANSI/ASME B16.2.1

### **Style AB-563**

EPDM (Black)

#### **Media**

- Animal and Vegetable oils
- Water
- Steam
- Oxygenated solvents



#### **Specifications**

Max. Temperature:	225	(° F)
Hardness Shore A	60	
Tensile Strength ASTM D-412	1000	(PSI)
Elongation	500	%

#### **Availability**

Full Face     Ring     1/16" Thick     1/8" Thick     1/4" Thick

#### **Benefits**

Commercial Grade

- Excellent for applications in which involve extreme temperature and or weather conditions. It's used extensively in high temperature installations.
- Offers ozone and chemical resistance as well as resistance to high temperatures.
- Also provides excellent electrical and dynamic properties.